

Technical Data Sheet

Product : LP. DP. Constell/ CCK-P

Sales Code: LPDJBGBCB0

Issued on: 21-04-2021

Top Side

- Constellation Jade
- Basis weight : 90 gsm \pm 4%
- Tensile strength (CD) : 2.1 kg/15 mm
- Tensile strength (MD) : 8.56 kg/15 mm

Adhesive

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 8.321 N
- Ball tack (JIS Z 0237:2000) acceptance value min. no 8
- 180° Peel strength test internal standard (PK/QC/21) acceptance value min 60 seconds.
- Service temperature range: -20°C to 70°C

Back Side Release Paper

- Clay Coated Kraft
- Basis weight: 135 \pm 4% gsm
- Thickness : 127 \pm 10 μ
- Tensile strength (MD) : 9.77 kg/15 mm
- Tensile strength (CD) : 6.32 kg/15 mm
- Release force label paper : 0 – 30 gf

Shelf Life

One year when stored at room temperature (25°C; 55%RH)

Other information

- Total thickness : 250 μ \pm 10%
- Paper type : 200 gsm
- Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

