

Head Office : Desa Betro, Sedati Sidoarjo 61253 Jawa Timur, Indonesia Ph : +62 31-8910519, 8910520 Fax: +62 31-8910521 Jakarta Office : Jl. Kapuk Kamal Raya No. 45 Komp. Pergud. Eco Park Unit AR-AS Jakarta Utara 14330 Ph : +62 21-2255552 Fax : +62 21-22555643

Technical Data Sheet

Product: LF. DP. PET Gold Matt / CCK -P

Sales Code : LFDUDHCBC0 Issued on : 24-01-2021

Top Side

- PET Gold Matt
- Appearance: Gold film with special treatment for digital printing
- Thickness: $36 \pm 3\mu$
- Tensile strength (CD) : 102.76 N/mm²
- Tensile strength (MD) : 120.0 N/mm²

Adhesive

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 8.112 N
- Ball tack (JIS Z 0237:2000) acceptance value min no. 8
- 180° Peel strength test internal standard (PK/QC/21) acceptance value min. 60 seconds.
- Service temperature range: -10°C to 70°C

Back Side Release Paper

- Clay Coated Kraft
- Basis weight: $135 \pm 4\%$ gsm
- Thickness : $127 \pm 10\mu$
- Tensile strength (MD) : 9.77 kg/15 mm
- Tensile strength (CD) : 6.32 kg/15 mm
- Release force label film : 0 30 gf

Shelf Life

One year when stored at room temperature (25°C; 55%RH)

Other information

- Total thickness $: 192\mu \pm 10\%$
- Paper type : 160 gsm
- Due to the wide variety of possible uses and applications, customer should determine the suitability for their specific purpose before to use.



