

Technical Data Sheet

Product: *LF. DIGIPRINT SATIN / CCK-P*

Sales Code: LFSDJCB0

Issued on : 21-04-2021

Top Side

- Satin
- Basis weight: 141 ± 4% gsm
- Tensile strength (CD) : 320.60 N/mm²
- Tensile strength (MD) : 292.12 N/mm²

Adhesive

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 6.821 N
- Ball tack (JIS Z 0237:2000) acceptance value min no.8
- 180° Peel strength test internal standard (PK/QC/21) acceptance value: min. 60 seconds.
- Service temperature range: -10°C to 70°C

Back Side Release Paper

- Clay Coated Kraft
- Basis weight: 135 ± 4% gsm
- Thickness : 127µ ± 10µ
- Tensile strength (MD) : 9.77 kg/15 mm
- Tensile strength (CD) : 6.32 kg/15 mm
- Release force label film: 0 – 30 gf

Shelf Life

One year when stored at room temperature (25°C; 55%RH)

Other information

- Total thickness : 315µ ± 10%
- Total grammage : 300 gsm ± 5%
- Paper type : 240 gsm
- Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

