

## Technical Data Sheet

**Product : LP. DP. Tintoretto/ CCK-P**

**Sales Code: LPDTBGCBC0**

**Issued on : 21-04-2021**

### Top Side

- Tintoretto Gesso
- Basis weight : 90 gsm  $\pm$  4%
- Tensile strength (CD) : 2.40 kg/15 mm
- Tensile strength (MD) : 7.96 kg/15 mm

### Adhesive

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing

### Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 9.031 N
- Ball tack (JIS Z 0237:2000) acceptance value min. no 8
- 180° Peel strength test internal standard (PK/QC/21) acceptance value min 60 seconds.
- Service temperature range: -20°C to 70°C

### Back Side Release Paper

- Clay Coated Kraft
- Basis weight: 135  $\pm$  4% gsm
- Thickness : 127  $\pm$  10 $\mu$
- Tensile strength (MD) : 9.77 kg/15 mm
- Tensile strength (CD) : 6.32 kg/15 mm
- Release force label paper : 0 – 30 gf

### Shelf Life

One year when stored at room temperature (25°C; 55%RH)

### Other information

- Total thickness : 264 $\mu$   $\pm$  10%
- Paper type : 200 gsm
- Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.