


Product

LP. HVS-A / RLY-B

Sales Code : LPHAEGC1C0 | Issued on : 10-11-2023



FACESTOCK

Color and appearance
 Basis weight
 Tensile strength (MD)
 Tensile strength (CD)

WOODFREE WHITE PAPER

White
 70 gsm ± 4%
 6.18 kg/15 mm
 2.43 kg/15 mm

ADHESIVE

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is paper tear.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
- Service temperature range -20°C to 70°C

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label paper

WOODFREE LIGHT YELLOW WITH PE (POLYETHYLENE) LAMINATION

72 gsm ± 4%
 89 µm ± 10 µm
 7.10 kg/ 15 mm
 3.69 kg/ 15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 189 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.