


TECHNICAL DATA SHEET

Product

LF. DP. PP TR / CCK-P



FACESTOCK BOPP (Biaxially Oriented Polypropylene) Film

Color and appearance Transparent film with special treatment for digital printing

Thickness $50 \, \mu m \, \pm \, 3 \, \mu m$

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

- 180° Peel strength test on stainless steel (FTM 1) is 8.482 N. **Application Test**

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -20°C to 70°C.

RELEASE LINER Clay Coated Kraft

Basis weight $126 \text{ gsm} \pm 4\%$ Thickness $138 \, \mu m \, \pm \, 10 \, \mu m$ Tensile strength (MD) 11.11 kg/15 mm Tensile strength (CD) 5.06 kg/15 mm

Release force label film Low release type: 0 - 30 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

 $210~\mu m~\pm~10\%$ Total thickness

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.





