


Product

LF. DP. PP WSG / CCK-P

Sales Code : LFDEDHCBC0 | Issued on : 30-10-2023



FACESTOCK

Color and appearance
 Thickness

BOPP (Biaxially Oriented Polypropylene) Film

White gloss film with special treatment for digital printing
 58 μm ± 3 μm

ADHESIVE

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 12.593 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
- Service temperature range -20°C to 70°C.

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

Clay Coated Kraft

126 gsm ± 4%
 138 μm ± 10 μm
 11.11 kg/15 mm
 5.06 kg/15 mm
 Low release type : 0 – 30 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 215 μm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.