


Product

LF. Emas / CCB

Sales Code : LFOGBGCAC0 | Issued on : 22-11-2023



FACESTOCK

Thickness	50 μm ± 3 μm
Tensile strength (MD)	87.88 N/mm ²
Tensile strength (CD)	149.34 N/mm ²

OPP METALIZE SILVER

ADHESIVE

Description	Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.
Application Test	<ul style="list-style-type: none"> - 180° Peel strength test on stainless steel (FTM 1) is 7.772 N. - Loop tack test (FTM 9) acceptance value min 6.0 N. - 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds. - Service temperature range -10°C to 70°C

RELEASE LINER

Basis weight	174 gsm ± 4%
Thickness	156 μm ± 10 μm
Tensile strength (MD)	13.05 kg/ 15 mm
Tensile strength (CD)	9.90 kg/ 15 mm
Release force label film	Low release type : 0 – 15 gf

CAST COAT BOARD WITH PE (POLYETHYLENE) LAMINATED

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 225 μm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

