


Product

LF. OPP TR-A / PET

Sales Code : LFODDHPAC0 | Issued on : 08-11-2023



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) FILM

Top treated for printability
 50 µm ± 3 µm
 81.81 kg/15 mm
 197.61 kg/15 mm

ADHESIVE

Description: Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test:

- 180° Peel strength test on stainless steel (FTM 1) is 16.299 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
- Service temperature range -10°C to 70°C

RELEASE LINER

Thickness
 Release force label film

POLYESTER TRANSPARENT

55 µm ± 5 µm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness: 96 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.