


**Product**

**LF. PET TR Inkjet / Glassine P-A**

Sales Code : LFJCAIW1C0 | Issued on : 21-11-2023



**FACESTOCK**

Color and appearance  
 Thickness  
 Tensile strength (MD)  
 Tensile strength (CD)

**POLYESTER TRANSPARENT**

Transparent film  
 50  $\mu\text{m} \pm 5 \mu\text{m}$   
 118.11 N/mm<sup>2</sup>  
 139.70 N/mm<sup>2</sup>

**ADHESIVE**

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 7.982 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
- Service temperature range -10°C to 70°C

**RELEASE LINER**

Basis weight  
 Thickness  
 Tensile strength (MD)  
 Tensile strength (CD)  
 Release force label film

**GLASSINE RELEASE PAPER**

60 gsm  $\pm 4\%$   
 55  $\mu\text{m} \pm 5 \mu\text{m}$   
 7.46 kg/ 15 mm  
 4.26 kg/ 15 mm  
 Low release type : 0 – 15 gf

**SHELF LIFE**

One year when stored at room temperature (25°C; 55%RH)

**OTHER INFORMATION**

Total thickness 121  $\mu\text{m} \pm 10\%$

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.