


Product

LF. PSM Inkjet / Glassine P-A

Sales Code : LFJHAIW1C0 | Issued on : 21-11-2023



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

PAPER LOOK FILM SPECIAL FOR INKJET PRINTER

Milky white matt film
 90 µm ± 5 µm
 104.86 N/mm²
 147.99 N/mm²

ADHESIVE

Description
 Application Test

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.
 - 180° Peel strength test on stainless steel (FTM 1) is 8.648 N.
 - Loop tack test (FTM 9) acceptance value min 6.0 N.
 - 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
 - Service temperature range -10°C to 70°C

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

GLASSINE RELEASE PAPER

60 gsm ± 4%
 55 µm ± 5 µm
 7.46 kg/ 15 mm
 4.26 kg/ 15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 167 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.