


TECHNICAL DATA SHEET

Product

LF. PVC TR Soft / CCB



FACESTOCK PVC FILM

Color and appearance Transparent soft Thickness 0.06 mm \pm 0.01 mm

Tensile strength (MD) 26.20 N/mm²
Tensile strength (CD) 40.51 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 14.457 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C

RELEASE LINER CAST COAT BOARD PE LAMINATED

 $\begin{array}{lll} \text{Basis weight} & 174 \text{ gsm} \pm 4\% \\ \text{Thickness} & 156 \text{ } \mu\text{m} \pm 10 \text{ } \mu\text{m} \\ \text{Tensile strength (MD)} & 13.05 \text{ } \text{kg/15mm} \\ \text{Tensile strength (CD)} & 9.90 \text{ } \text{kg/15mm} \end{array}$

Release force label film Low release type : 0-15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 232 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









