


Product

LF. Satin / CCB

Sales Code : LFSTEJCAC0 | Issued on : 21-11-2023



FACESTOCK

Basis weight
 Tensile strength (MD)
 Tensile strength (CD)

SATIN

141 gsm ± 4%
 292.12 N/mm²
 320.60 N/mm²

ADHESIVE

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 12.698 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
- Service temperature range -10°C to 70°C

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

CAST COAT BOARD PE LAMINATED

174 gsm ± 4%
 156 µm ± 10 µm
 13.05 kg/ 15 mm
 9.90 kg/ 15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 301 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.