


Product

LF. Taffeta / CCB

Sales Code : LFTFEICAC0 | Issued on : 21-11-2023



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

TAFFETA FILM

Milky white, emboss film
 112 $\mu\text{m} \pm 10 \mu\text{m}$
 160.55 N/mm^2
 78.85 N/mm^2

ADHESIVE

Description: Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test:

- 180° Peel strength test on stainless steel (FTM 1) is 9.816 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
- Service temperature range -10°C to 70°C

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

CAST COAT BOARD PE LAMINATED

174 $\text{gsm} \pm 4\%$
 156 $\mu\text{m} \pm 10 \mu\text{m}$
 13.05 $\text{kg}/15 \text{ mm}$
 9.90 $\text{kg}/15 \text{ mm}$
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 293 $\mu\text{m} \pm 10\%$

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.