

# **TECHNICAL DATA SHEET**

## **Product**





## FACESTOCK PVC FILM

Appearance Transparent, soft Thickness 80  $\mu$ m  $\pm$  10  $\mu$ m Tensile strength (MD) 51.39 N/mm<sup>2</sup> Tensile strength (CD) 38.19 N/mm<sup>2</sup>

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for large format label film.

Application Test - 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is

4.945 N.

- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is

8.826 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- Service temperature range -10°C to 70°C

### RELEASE LINER CLAY COATED KRAFT

 $\begin{array}{lll} Basis \ weight & 120 \ gsm \ \pm \ 4\% \\ Thickness & 125 \ \mu m \ \pm \ 10 \ \mu m \\ Tensile \ strength \ (MD) & 10.34 \ kg/ \ 15 \ mm \\ Tensile \ strength \ (CD) & 4.57 \ kg/ \ 15 \ mm \\ \end{array}$ 

Release force label paper Low release type: 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

## OTHER INFORMATION

Total thickness 230  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









