


# **TECHNICAL DATA SHEET**

### **Product**

## LP. Art Paper-A / RLY-B



FACESTOCK ART PAPER

Color and appearance White

Basis weight 80 gsm  $\pm$  4% Thickness 63  $\mu$ m  $\pm$  5  $\mu$ m Tensile strength (MD) 4.42 kg/15 mm Tensile strength (CD) 1.89 kg/15 mm

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -20°C to 70°C

## RELEASE LINER WOODFREE LIGHT YELLOW WITH PE (POLYETHYLENE) LAMINATION

 $\begin{array}{lll} \text{Basis weight} & 72 \text{ gsm} \pm 4\% \\ \text{Thickness} & 89 \text{ } \mu\text{m} \pm 10 \text{ } \mu\text{m} \\ \text{Tensile strength (MD)} & 3.69 \text{ } \text{kg/} 15 \text{ } \text{mm} \\ \text{Tensile strength (CD)} & 7.10 \text{ } \text{kg/} 15 \text{ } \text{mm} \\ \end{array}$ 

Release force label paper Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

## **OTHER INFORMATION**

Total thickness 162  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









