

# **TECHNICAL DATA SHEET**

### **Product**

# LP. Art Paper-B / Glassine P-B



FACESTOCK ART PAPER

Color and appearance White

Basis weight 70 gsm  $\pm$  4% Thickness 57  $\mu$ m  $\pm$  5  $\mu$ m Tensile strength (MD) 4.69 kg/15 mm Tensile strength (CD) 1.91 kg/15 mm

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -20°C to 70°C

### RELEASE LINER GLASSINE RELEASE PAPER

 $\begin{array}{lll} \mbox{Basis weight} & 40 \mbox{ gsm} \pm 4\% \\ \mbox{Thickness} & 40 \mbox{ } \mu m \pm 5 \mbox{ } \mu m \\ \mbox{Tensile strength (MD)} & 5.71 \mbox{ kg/ } 15 \mbox{ mm} \\ \mbox{Tensile strength (CD)} & 2.63 \mbox{ kg/ } 15 \mbox{ mm} \\ \end{array}$ 

Release force label paper Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

## **OTHER INFORMATION**

Total thickness 118  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









