


TECHNICAL DATA SHEET

Product

LP. Cast Coated / Glassine P-E



FACESTOCK CAST COATED PAPER

Color and appearance White

Basis weight 75 gsm \pm 4% Thickness 77 μ m \pm 5 μ m Tensile strength (MD) 4.35 kg/15 mm Tensile strength (CD) 2.11 kg/15 mm

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 45 seconds.

- Service temperature range -20°C to 70°C

RELEASE LINER GLASSINE RELEASE PAPER

 $\begin{array}{lll} Basis \ weight & 54 \ gsm \ \pm \ 4\% \\ Thickness & 50 \ \mu m \ \pm \ 5 \ \mu m \\ Tensile \ strength \ (MD) & 6.37 \ kg/ \ 15 \ mm \\ Tensile \ strength \ (CD) & 3.78 \ kg/ \ 15 \ mm \\ \end{array}$

Release force label paper Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 143 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









