


# **TECHNICAL DATA SHEET**

#### **Product**

## LP. Cast Coated / RLY-B (MASTER)



#### FACESTOCK CAST COATED PAPER

Color and appearance White

Basis weight 80 gsm  $\pm$  4% Thickness 89  $\mu$ m  $\pm$  5  $\mu$ m Tensile strength (MD) 3.69 kg/15 mm Tensile strength (CD) 1.67 kg/15 mm

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -20°C to 70°C

#### RELEASE LINER WOODFREE LIGHT YELLOW WITH PE (POLYETHYLENE) LAMINATION

 $\begin{array}{lll} Basis \ weight & 72 \ gsm \ \pm \ 4\% \\ Thickness & 89 \ \mu m \ \pm \ 10 \ \mu m \\ Tensile \ strength \ (MD) & 7.10 \ kg/ \ 15 \ mm \\ Tensile \ strength \ (CD) & 3.69 \ kg/ \ 15 \ mm \\ \end{array}$ 

Release force label paper Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

### **OTHER INFORMATION**

Total thickness 178  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.







