


TECHNICAL DATA SHEET

Product

LP. Kraft / RLY-B



FACESTOCK KRAFT PAPER

Basis weight $60 \text{ gsm} \pm 4\%$ Tensile strength (MD) 6.01 kg/15mmTensile strength (CD) 2.02 kg/15mm

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -20°C to 70°C

RELEASE LINER WOODFREE LIGHT YELLOW WITH PE (POLYETHYLENE) LAMINATION

 $\begin{array}{lll} \mbox{Basis weight} & 72 \mbox{ gsm} \pm 4\% \\ \mbox{Thickness} & 89 \mbox{ } \mu m \mbox{ } \pm 10 \mbox{ } \mu m \\ \mbox{Tensile strength (MD)} & 7.10 \mbox{ kg/15mm} \\ \mbox{Tensile strength (CD)} & 3.69 \mbox{ kg/15mm} \end{array}$

Release force label paper Low release type : 0-15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 183 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









