


Product

LP. Thermal Paper / Glassine P-E

Sales Code : LPTCAGE1C000 | Issued on : 28-11-2023



FACESTOCK

Basis weight
 Tensile strength (MD)
 Tensile strength (CD)

THERMAL PAPER

63 gsm ± 6%
 4.97 kg/15 mm
 3.65 kg/15 mm

ADHESIVE

Description: Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test:

- 180° Peel strength test on stainless steel (FTM 1) is paper tear.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
- The printed image contrast will be lacked if contact with water directly.

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label paper

GLASSINE RELEASE PAPER

54 gsm ± 4%
 50 µm ± 5 µm
 6.37 kg/ 15 mm
 3.78 kg/ 15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness: 124 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.