

**Product**

**LF. Digiprint PP Gold / CCK (IND)**

Sales Code : LFDQDHCBC0 | Issued on : 06-12-2023



**FACESTOCK**

Color and appearance  
Thickness  
Tensile strength (MD)  
Tensile strength (CD)

**BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) METALIZE GOLD FILM**

Gold film with special treatment for digital printing  
50  $\mu\text{m} \pm 3 \mu\text{m}$   
87.88 N/mm<sup>2</sup>  
149.34 N/mm<sup>2</sup>

**ADHESIVE**

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 6.342 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
- Service temperature range -10°C to 70°C

**RELEASE LINER**

Basis weight  
Thickness  
Tensile strength (MD)  
Tensile strength (CD)  
Release force label paper

**CLAY COATED KRAFT**

126 gsm  $\pm 4\%$   
138  $\mu\text{m} \pm 10 \mu\text{m}$   
11.11 kg/ 15 mm  
5.06 kg/ 15 mm  
Low release type : 0 – 30 gf

**SHELF LIFE**

One year when stored at room temperature (25°C; 55%RH)

**OTHER INFORMATION**

Total thickness 226  $\mu\text{m} \pm 10\%$   
Total grammage 191 gsm  $\pm 5\%$

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.