


TECHNICAL DATA SHEET

Product

LF. Digiprint PP WSG / CCK-P (IND)

Sales Code : LFDKDHCBC0 | Issued on : 06-12-2023



FACESTOCK

BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) FILM

Color and appearance Thickness

ADHESIVE

Description

Application Test

White gloss with special treatment for HP Indigo 58 $\mu m~\pm~3~\mu m$

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for digital printing.

- 180° Peel strength test on stainless steel (FTM 1) is 6.711 N.
 - Loop tack test (FTM 9) acceptance value min 6.0 N.
 - 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
 - Service temperature range -10°C to 70°C

RELEASE LINER

CLAY COATED KRAFT

 $126 \text{ gsm} \pm 4\%$

 $138 \, \mu m \pm 10 \, \mu m$

Basis weight Thickness Tensile strength (MD) Tensile strength (CD) Release force label paper

11.11 kg/ 15 mm 5.06 kg/ 15 mm Low release type : 0 – 30 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness226 μm ± 10%Total grammage191 gsm ± 5%Paper type160 gsm

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.







