


TECHNICAL DATA SHEET

Product

LF. Digiprint PP WSM / CCK-P (IND)



FACESTOCK PAPER LOOK FILM

Color and appearance White matte film with special treatment for HP Indigo

Thickness 80 μ m \pm 5 μ m

Tensile strength (MD) 51.63 N/mm²

Tensile strength (CD) 172.57 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for digital printing.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 8.649 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C

RELEASE LINER CLAY COATED KRAFT

 $\begin{array}{lll} \text{Basis weight} & 126 \text{ gsm} \pm 4\% \\ \text{Thickness} & 138 \text{ } \mu\text{m} \pm 10 \text{ } \mu\text{m} \\ \text{Tensile strength (MD)} & 11.11 \text{ } \text{kg}/\text{ } 15 \text{ } \text{mm} \\ \text{Tensile strength (CD)} & 5.06 \text{ } \text{kg}/\text{ } 15 \text{ } \text{mm} \\ \end{array}$

Release force label paper Low release type: 0 - 30 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 261 μ m \pm 10% Total grammage 211 gsm \pm 5% Paper type 170 gsm

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.







