


**Product**

**LF. OPP PSM RMV / Glassine BM**

Sales Code : LFOBMEM1C0 | Issued on : 17-11-2023



**FACESTOCK**

Color and appearance  
 Thickness  
 Tensile strength (MD)  
 Tensile strength (CD)

**PAPER LOOK FILM**

White matt film  
 80 µm ± 5 µm  
 51.63 N/mm<sup>2</sup>  
 172.57 N/mm<sup>2</sup>

**ADHESIVE**

Description: Removable adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock

Application Test:

- 180° Peel strength test on stainless steel (FTM 1) is 4.272 N.
- 180° Peel strength test internal standard (PK/QC/21) max. 90 seconds.
- Service temperature range -20°C to 70°C

**RELEASE LINER**

Basis weight  
 Thickness  
 Tensile strength (MD)  
 Tensile strength (CD)  
 Release force label film

**GLASSINE RELEASE PAPER**

60 gsm ± 4%  
 55 µm ± 5 µm  
 6.81 kg/ 15 mm  
 3.58 kg/ 15 mm  
 Low release type : 0 – 15 gf

**SHELF LIFE**

One year when stored at room temperature (25°C; 55%RH)

**OTHER INFORMATION**

Total thickness: 151 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.