


TECHNICAL DATA SHEET

Product

LF-VTC80-CCKP "CAMEL"



FACESTOCK PVC TRANSLUCENT EMBOSSING

Thickness $0.08 \text{ mm} \pm 0.01 \text{ mm}$

Tensile strength (MD) 26.06 N/mm²
Tensile strength (CD) 24.67 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is

9.900 N.

- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is

13.494 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- Service temperature range -10°C to 70°C.

RELEASE LINER CLAY COATED KRAFT

Basis weight 120 gsm \pm 4% Thickness 125 μ m \pm 10 μ m Tensile strength (MD) 10.34 kg/15 mm Tensile strength (CD) 4.57 kg/15 mm

Release force label film Low release type : 0-15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 260 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









