


Product

LF-VTG80-CCKP “CAMEL”

Sales Code : LFLBFGCBC0 | Issued on : 06-12-2023



FACESTOCK

Appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

PVC FILM

Transparent, soft
 0.08 mm ± 0.01 mm
 51.39 N/mm²
 38.19 N/mm²

ADHESIVE

Description Solvent base adhesive is acrylic solution which insoluble in water and special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is 4.945 N.
- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is 8.826 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- Service temperature range -10°C to 70°C.

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

CLAY COATED KRAFT

120 gsm ± 4%
 125 µm ± 10 µm
 10.34 kg/15 mm
 4.57 kg/15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 230 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

