

Product

LF-VTG80-PET23 "CAMEL"

Sales Code : LFLBFGPBC0 | Issued on : 17-01-2025



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

PVC FILM

Transparent and soft
 0.08 mm ± 0.01 mm
 51.39 N/mm²
 38.19 N/mm²

ADHESIVE

Description

Solvent base adhesive is acrylic solution which insoluble in water and special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is 9.261 N.
- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is 11.162 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- Service temperature range -10°C to 70°C.

RELEASE LINER

Thickness
 Release force label film

POLYESTER TRANSPARENT

23 µm ± 3 µm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 123 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

