


TECHNICAL DATA SHEET

Product

LF-VWG100-CCKP "CAMEL"



FACESTOCK PVC FILM

Appearance White, soft

Thickness 0.10 mm \pm 0.01 mm

Tensile strength (MD) 40.74 N/mm²
Tensile strength (CD) 38.76 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is

3.945 N.

- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is

8.854 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- Service temperature range -10°C to 70°C.

RELEASE LINER CLAY COATED KRAFT

 $\begin{array}{lll} Basis \ weight & 120 \ gsm \ \pm \ 4\% \\ Thickness & 125 \ \mu m \ \pm \ 10 \ \mu m \\ Tensile \ strength \ (MD) & 10.34 \ kg/15 \ mm \\ Tensile \ strength \ (CD) & 4.57 \ kg/15 \ mm \end{array}$

Release force label film Low release type: 0 – 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 250 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









