


## **TECHNICAL DATA SHEET**

#### **Product**

### LF-VWG80-CCKP-BO "CAMEL"



#### FACESTOCK PVC FILM

Appearance White, soft

Thickness  $0.08 \text{ mm} \pm 0.01 \text{ mm}$ 

Tensile strength (MD) 46.16 N/mm<sup>2</sup>
Tensile strength (CD) 32.21 N/mm<sup>2</sup>

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label film of PVC large format containing a plasticizer-resistant that does not leave any residue on the substrate upon

debonding.

Application Test - 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is

11.894 N.

- 180° Peel strength test on stainless steel (FTM 1) after aging 24 hours is

14.227 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- Service temperature range -10°C to 70°C.

#### RELEASE LINER CLAY COATED KRAFT

Basis weight 120 gsm  $\pm$  4% Thickness 125  $\mu$ m  $\pm$  10  $\mu$ m Tensile strength (MD) 10.34 kg/15 mm Tensile strength (CD) 4.57 kg/15 mm

Release force label film Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)













# **TECHNICAL DATA SHEET**

#### **OTHER INFORMATION**

Total thickness 230  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.







