


TECHNICAL DATA SHEET

Product

LF. DP-PETMG36-CCKP-IND "CAMEL"



FACESTOCK PET METALIZE

Color and appearance Metalize film with special treatment for digital printing

Thickness 36 μ m \pm 3 μ m Tensile strength (MD) 95.38 N/mm² Tensile strength (CD) 152.60 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for digital printing.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 9.721 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C

RELEASE LINER CLAY COATED KRAFT

Basis weight 126 gsm \pm 4% Thickness 138 μ m \pm 10 μ m Tensile strength (MD) 11.11 kg/15 mm Tensile strength (CD) 5.06 kg/15 mm

Release force label film Low release type : 0 - 30 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 195 μ m \pm 10% Total grammage 200 gsm \pm 5% Paper type 160 gsm

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









