

TECHNICAL DATA SHEET

Product

LF. INKJET WG-WG58 "CAMEL"



FACESTOCK BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) FILM

Color and appearance White top coated for printability

Thickness 90 μ m \pm 6 μ m Tensile strength (MD) 92.24 N/mm² Tensile strength (CD) 149.96 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 13.581 N.

- Loop tack test (FTM 9) acceptance value min 7.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.

- Service temperature range -10°C to 70°C

RELEASE LINER GLASSINE RELEASE PAPER

 $\begin{array}{lll} \text{Basis weight} & 59 \text{ gsm} \pm 4\% \\ \text{Thickness} & 52 \text{ } \mu\text{m} \pm 5 \text{ } \mu\text{m} \\ \text{Tensile strength (MD)} & 8.27 \text{ kg/ } 15 \text{ } \text{mm} \\ \text{Tensile strength (CD)} & 3.53 \text{ kg/ } 15 \text{ } \text{mm} \\ \end{array}$

Release force label film Low release type : 0-15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness $163 \mu m \pm 10\%$

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









