


Product

LF. PET TR INKJET-WGL58 "CAMEL"

Sales Code : LFJCAIW1C0 | Issued on : 22-01-2025



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

POLYESTER TRANSPARANT

Transparent Film
 50 µm ± 3 µm
 118.11 N/mm²
 139.70 N/mm²

ADHESIVE

Description

Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 8.820 N.
- Loop tack test (FTM 9) acceptance value min 7.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 90 seconds.
- Service temperature range -10°C to 70°C

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

GLASSINE RELEASE PAPER

59 gsm ± 4%
 52 µm ± 5 µm
 8.27 kg/ 15 mm
 3.53 kg/ 15 mm
 Low release type : 0 – 15 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 121 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

