


TECHNICAL DATA SHEET

Product

LP-CC80-RY82P "CAMEL"



FACESTOCK CAST COATED PAPER

Color and appearance White

Basis weight 80 gsm \pm 4% Thickness 89 μ m \pm 5 μ m Tensile strength (MD) 4.33 kg/15 mm Tensile strength (CD) 2.56 kg/15 mm

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is paper tear.

- Loop tack test (FTM 9) is 10.006 N (Acceptance value min 6.0 N).

- 180° Peel strength test internal standard (PK/QC/21) is 441 seconds

(Acceptance value min. 90 seconds).

- Service temperature range -20°C to 70°C

RELEASE LINER WOODFREE YELLOW WITH PE (POLYETHYLENE) LAMINATION

 $82 \text{ gsm} \pm 4\%$ Thickness $104 \text{ } \mu\text{m} \pm 10 \text{ } \mu\text{m}$ Tensile strength (MD) 7.68 kg/15 mm Tensile strength (CD) 4.41 kg/15 mm

Release force label paper Low release type : 0 - 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 198 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









