


# **TECHNICAL DATA SHEET**

### **Product**

# LPDP-CONST-CCKP " CAMEL"



### FACESTOCK CONSTELLATION JADE

Basis weight 90 gsm  $\pm$  4% Tensile strength (MD) 8.56 kg/15mm Tensile strength (CD) 2.10 kg/15mm

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for digital printing.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 8.321 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

-  $180^{\circ}$  Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C.

## RELEASE LINER CLAY COATED KRAFT

Basis weight 126 gsm  $\pm$  4% Thickness 138  $\mu$ m  $\pm$  10  $\mu$ m Tensile strength (MD) 11.11 kg/15 mm Tensile strength (CD) 5.06 kg/15 mm

Release force label film  $\qquad \qquad$  Low release type : 0 – 30 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

#### **OTHER INFORMATION**

Total thickness 261  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









