


TECHNICAL DATA SHEET

Product





FACESTOCK COROLLA WHITE

Basis weight 90 gsm \pm 4% Tensile strength (MD) 7.96 kg/15mm Tensile strength (CD) 2.30 kg/15mm

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for digital printing.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 10.330 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C.

RELEASE LINER CLAY COATED KRAFT

Basis weight $126 \text{ gsm} \pm 4\%$ Thickness $138 \ \mu m \ \pm \ 10 \ \mu m$ Tensile strength (MD) 11.11 kg/15 mm Tensile strength (CD) 5.06 kg/15 mm

Release force label film Low release type: 0 - 30 gf

One year when stored at room temperature (25°C; 55%RH) SHELF LIFE

OTHER INFORMATION

 $254 \mu m \pm 10\%$ Total thickness

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









