


# **TECHNICAL DATA SHEET**

#### **Product**

## LF-VTC80-CCKP "CAMEL"



#### FACESTOCK PVC TRANSLUCENT EMBOSSING

Thickness 0.08 mm  $\pm$  0.01 mm

Tensile strength (MD) 26.06 N/mm<sup>2</sup>
Tensile strength (CD) 24.67 N/mm<sup>2</sup>

#### **ADHESIVE**

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) after aging 20 minutes is

9.900 N.

-  $180^{\circ}$  Peel strength test on stainless steel (FTM 1) after aging 24 hours is

13.494 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- Service temperature range -10°C to 70°C.

#### RELEASE LINER CLAY COATED KRAFT

Basis weight 120 gsm  $\pm$  4% Thickness 125  $\mu$ m  $\pm$  10  $\mu$ m Tensile strength (MD) 10.34 kg/15 mm Tensile strength (CD) 4.57 kg/15 mm

Release force label film  $\qquad \qquad$  Low release type : 0 – 15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

### **OTHER INFORMATION**

Total thickness 260  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









