

**Product**

**LF. PPTR50-PET23WT "CAMEL"**

Sales Code : LFODLHPAC0 | Issued on : 20-01-2025



**FACESTOCK**

Color and appearance  
 Thickness  
 Tensile strength (MD)  
 Tensile strength (CD)

**BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) FILM**

Top treated for printability  
 50 µm ± 3 µm  
 81.81 N/mm<sup>2</sup>  
 197.61 N/mm<sup>2</sup>

**ADHESIVE**

Description: Solvent base removable adhesive is acrylic solution which insoluble in water and special adhesive for removable application.

Application Test:

- 180° Peel strength test on stainless steel (FTM 1) is 5.357 N.
- 180° Peel strength test internal standard (PK/QC/21) max. 45 seconds.
- Service temperature range -10°C to 70°C

**RELEASE LINER**

Thickness  
 Release force label film

**POLYESTER TRANSPARENT**

23 µm ± 3 µm  
 Low release type : 0 – 15 gf

**SHELF LIFE**

One year when stored at room temperature (25°C; 55%RH)

**OTHER INFORMATION**

Total thickness 95 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

