

# **TECHNICAL DATA SHEET**

#### Product

# LF. PPWM80-BG60RMV "CAMEL"

Sales Code : LFOBMEM1C0 | Issued on : 16-01-2025



Color and appearance Thickness Tensile strength (MD) Tensile strength (CD)

#### ADHESIVE

Description

Application Test

80 μm ± 5 μm 51.63 N/mm<sup>2</sup> 172.57 N/mm<sup>2</sup>

Removable adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock

- 180° Peel strength test on stainless steel (FTM 1) is 4.272 N.
- 180° Peel strength test internal standard (PK/QC/21) max. 90 seconds.
- Service temperature range -20°C to 70°C

**GLASSINE RELEASE PAPER** 

Low release type : 0 - 15 gf

#### **RELEASE LINER**

Basis weight Thickness Tensile strength (MD) Tensile strength (CD) Release force label film

## SHELF LIFE

Total thickness

One year when stored at room temperature (25°C; 55%RH)

## **OTHER INFORMATION**

151  $\mu$ m ± 10%

 $60 \text{ gsm} \pm 4\%$ 

 $55 \,\mu m \pm 5 \,\mu m$ 

6.81 kg/ 15 mm

3.58 kg/ 15 mm

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.







