


TECHNICAL DATA SHEET

Product

LF. VTS60-CCBP "CAMEL"



FACESTOCK PVC FILM

Color and appearance Transparent soft

Thickness $0.06 \text{ mm} \pm 0.01 \text{ mm}$

Tensile strength (MD) 26.20 N/mm²
Tensile strength (CD) 40.51 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 12.313 N.

- Loop tack test (FTM 9) is 11.627 N (acceptance value min 6.0 N).

- 180° Peel strength test internal standard (PK/QC/21) is 824 seconds (min.

60 seconds).

- Service temperature range -10°C to 70°C

RELEASE LINER CAST COAT BOARD PE LAMINATED

Basis weight 170 gsm \pm 4% Thickness 148 μ m \pm 10 μ m Tensile strength (MD) 9.97 kg/15mm Tensile strength (CD) 7.87 kg/15mm

Release force label film Low release type : 0-15 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 225 μ m \pm 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









