


## **TECHNICAL DATA SHEET**

## **Product**

## LFDP-PPMG50-CCKP "CAMEL"



FACESTOCK BOPP (BIAXIALLY ORIENTED POLYPROPYLENE) METALIZE SILVER

**FILM** 

Color and appearance Metalize film with special treatment for digital printing

Thickness 50  $\mu$ m  $\pm$  3  $\mu$ m Tensile strength (MD) 152.60 N/mm<sup>2</sup> Tensile strength (CD) 95.38 N/mm<sup>2</sup>

**ADHESIVE** 

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer

which is a special adhesive for label stock.

Application Test - 180° Peel strength test on stainless steel (FTM 1) is 6.486 N.

- Loop tack test (FTM 9) acceptance value min 6.0 N.

- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.

- Service temperature range -10°C to 70°C.

RELEASE LINER CLAY COATED KRAFT

 $\begin{array}{lll} \text{Basis weight} & 126 \text{ gsm} \pm 4\% \\ \text{Thickness} & 138 \text{ } \mu\text{m} \pm 10 \text{ } \mu\text{m} \\ \text{Tensile strength (MD)} & 11.11 \text{ } \text{kg/15 mm} \\ \text{Tensile strength (CD)} & 5.06 \text{ } \text{kg/15 mm} \\ \end{array}$ 

Release force label film  $\qquad$  Low release type : 0 – 30 gf

SHELF LIFE One year when stored at room temperature (25°C; 55%RH)

**OTHER INFORMATION** 

Total thickness 205  $\mu$ m  $\pm$  10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.









