


Product

LFDP-TAFFETA-CCKP “CAMEL”

Sales Code : LFDTDICBC0 | Issued on : 20-01-2025



FACESTOCK

Color and appearance
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)

TAFETA FILM

Milky white and emboss film
 76 µm ± 4%
 78. N/mm²
 160.55 N/mm²

ADHESIVE

Description Camel adhesive formulation is aqueous dispersion of an acrylic copolymer which is a special adhesive for label stock.

Application Test

- 180° Peel strength test on stainless steel (FTM 1) is 7.263 N.
- Loop tack test (FTM 9) acceptance value min 6.0 N.
- 180° Peel strength test internal standard (PK/QC/21) min. 60 seconds.
- Service temperature range -10°C to 70°C.

RELEASE LINER

Basis weight
 Thickness
 Tensile strength (MD)
 Tensile strength (CD)
 Release force label film

CLAY COATED KRAFT

126 gsm ± 4%
 138 µm ± 10 µm
 11.11 kg/15 mm
 5.06 kg/15 mm
 Low release type : 0 – 30 gf

SHELF LIFE

One year when stored at room temperature (25°C; 55%RH)

OTHER INFORMATION

Total thickness 273 µm ± 10%

Due to the wide variety of possible uses and applications, customers should determine the suitability for their specific purpose before to use.

